



**TBJ SEALING
TECHNOLOGIES**



**TBJ-UTEX
INDUSTRIES**

AEROLITE GS7004

Packing & Gaskets

Graphite Laminate Sheet With 316 Stainless Steel Foil Reinforcement

DS003-03

Material Profile :

- Made of expanded graphite reinforced with flat stainless steel SUS316 (0.05mm, thick), used as gasket material

Typical application :

- AEROLITE GS7004 is suitable for use in general gasket applications and can be used for sealing steam and most chemicals with the exception of oxidising agents.
- Maximum recommended temperature : 500°C (Oxidizing media)
- Maximum recommended temperature : 700°C (Inert media)
- Maximum recommended pressure : 55 Bar (800 psi)

Property	Standard	Unit	Value		
Thickness		mm	1.5	2.0	3.0
Density (graphite)		g/cm ³	1.0	1.0	1.0
Compressibility	ASTM F36/A	%	25-45	25-45	25-45
Recovery	ASTM F36/A	%	≥10	≥10	≥10
Leakage rate	DIN 3535	ml/min	≤1.0	≤1.0	≤1.0
Fluid resistant :	ASTM F146				
•ASTM3# oil 150°C, 5h					
Weight increse		%	<15	<15	<15
Thickness increase		%	≤6	≤6	≤6
• <u>LLC50% 100°C,22h</u>					
Weight increase		%	<15	<15	<15
Thickness increase		%	≤6	≤6	≤6
Sulfur content	ASTM C 816	ppm	≈1300	≈1300	≈1300
Leachable Chloride content	ASTM F1277	ppm	≤50	≤50	≤50
Carbon content	JB/T 9141.6	%	≥98.5	≥98.5	≥98.5
Fluoride content		ppm	≤30	≤30	≤30

Data reported corresponds to laboratory and field tests typical results. Technical guidance are pleased to assistant when requested.

Supply data :

- Size in mm: 500 x 1000, 1000 x 1000, 1500 x 1500 (Overlapped Joint and/or Laser Welding Flat Joint)
- Thickness: 0.5 - 7.0mm
- Special size and thickness upon request.
- Reinforcing steel, SUS316L (DIN1.4404) and SUS304 (DIN 1.4301) are all in stocks.



NOTE:

ALL INFORMATIONS AND RECOMMENDATIONS GIVEN IN THIS BROCHURE ARE CORRECT TO THE BEST OF OUR KNOWLEDGE. SINCE CONDITIONS OF USE ARE BEYOND OUR CONTROL. THE INFORMATIONS PROVIDED AND ONLY SERVE AS A GUIDELINE. USERS MUST SATISFY THEMSELVES THAT PRODUCTS ARE SUITABLE FOR THE INTENDED PROCESS AND USES.

WE RESERVE THE RIGHT TO CHANGE PRODUCT DESIGN AND PROPERTIES WITHOUT NOTICE

